

WALL PANELS



Custom precast concrete wall panels add a touch of sophistication while serving as abstract works of art. Create a wall panel with undulating heights and widths, radial or straight. Choose from different profiles like block or tapered and add recesses or reveals for lighting. With so many options for wall panels, your custom design is just steps away.

Standard color options include Weatherstone, Light Grind, Ground & Polished and Acid Wash and can be viewed at WausauTile.com.

| PROPERTY | ADVANCED TESTING VALUE | TEST METHOD |
|---------------------------|--|--|
| Compression Strength | Wausau Tile standard is 5000 PSI at 28 days. | ASTM C39 |
| Water Absorption | Wausau Tile standard is less than 6%. | ASTM C642 |
| Flexural Strength | Non-Standard | ASTM C78 (3rd party test: American Engineering) |
| C373 Water Absorption | Not-Applicable | |
| C482 Bond Strength | Not-Applicable | |
| C485 Warpage Edge | Tolerance of +/- 1/8" | 100% Visual inspection of product, Straight edge confirmation as needed. |
| C485 Warpage Diagonal | Tolerance of +/- 1/8" | 100% Visual inspection of product, Straight edge confirmation as needed. |
| C499 Nominal Size | Tolerance of +/- 1/8" | 100% Inspection, Measurements verified against fabrication drawings. |
| C499 Thickness | Tolerance of +/- 1/8" | 100% Inspection, Measurements verified against fabrication drawings. |
| Dynamic DCOF | Not-Applicable | |
| ANSI A173.1 Section 9.6.1 | Not-Applicable (Tile only) | |
| Avg. Polished Finish | 100% Visual Inspection | Visually compare product to control sample |
| Avg. Honed Finish | 100% Visual Inspection | Visually compare product to control sample |
| Freeze/Thaw | Non-Standard | ASTM C666 (3rd Party, American Engineering) |
| Center Load | Not-Applicable (Pavers only) | |

CALL FOR FURTHER DETAILS & PRICING.